



Polishing Powder

UCOLIN^{COM}

Rare earth Cerium Oxide CeO₂ Rhinestone Polishing Powder -668-1

REO≥87%

CeO₂/REO≥82%

Fluorine content: 2.8%

Average granularity D50: 1.4μm

Granularity: 1200# -1500#

PH value: 7

Color: Light yellow

Applicable fields:

This serial of Rare earth Cerium Oxide CeO₂ rhinestone polishing powder has been widely applied in the polishing of various rhinestones and hot-fix rhinestones.

Rare earth Cerium Oxide CeO₂ rhinestone polishing powder is especially used for the polishing of rhinestones and hot-fix rhinestones. Compared with other normal rhinestone polishing powder, this Rare earth Cerium Oxide CeO₂ rhinestone polishing powder can decrease 11% of the Rare earth polishing powder liquid concentration, and the polishing effect can increase 35%. Besides, the gloss finish of the finished product can get higher grade, and the Rare earth polishing powder's life time increases 30%.

Main features:

1. High polishing speed, great grinding ability, no scratch.
2. Small amount and low concentration of polishing powder can make the optimum polishing effect.
3. Good polishing brightness, High content of Cerium Oxide, reasonable collocation of the crudeness and fineness, applicable for the polishing of various rhinestones and crystals.
4. Good suspensibility, not easy to settle. And even if the powder is settled for a long time, it is still easy to stir up without bubbles.
5. Environmental-friendly, neutral in PH value, water-fast, good adhesive force, easy to wash, no odors, humidity-resistant, long life time.

Packing:

Inner packing: plastic bag,

Weight: 5kg per bag.

Outer packing: cardboard carton, cardboard barrel, plastic barrel

Net Weight:

20kg/ cardboard carton, 25kg/ cardboard carton,
40kg /cardboard barrel, 50kg /cardboard barrel,
20kg/ plastic barrel, 25kg/ plastic barrel.

UCOLIN.COM

All rights reserved by UCOLIN GLAZING SUPPORT:

www.Ucolin.com

Main Products: Silicone vacuum bag for EVA laminating furnace, Silicone Sheet, Glass Edging Wheels, Polishing Powders.

Zac Lynn
uc@ucolin.com